



PRODUCT SPECIFICATIONS

DURACORD 1000™

WEIGHT: 438g/m²
(AS 2001.2.13)

TENSILE STRENGTH: WARP – 3310 N/50mm
(AS 2001.2.3) WEFT – 2909 N/50mm

WING RIP TEAR: WARP – 226N
(AS 2001.2.10) WEFT – 174N

WATER RESISTANCE: 10kPa min.
(AS 2001.2.17)

CONE TEST: PASS
(AS 2001.2.18)

FLEX ABRASION: 6,000 cycles – no penetration
(DEFAUST5037 A24)

COLOUR FASTNESS: Light - 6 (AS 2001.4.2)
Wet Rub - 5 (AS 2001.4.3)
Dry Rub - 5 (AS 2001.4.3)

SPRAY RATING: 90
(AS 2011.2.16)

COLOURS: Black, Navy, Hunter Green, Grey, Aus Cam DP
Other colours Made to Order –
minimum 500 metres per colour.